

Technical datasheet for:

## speed•pipe<sup>®</sup>-ground 20x2.5 €€



speed•pipe°-groun		
	General data	
Item	speedpipe-ground 20x2.5	
Description	speedpipe-ground for the direct bury	
Production length on spool (1200x700mm)	1400m	
Weight	approx. 0.132 kg/m	
Total weight	approx. 225 kg (including spool)	
Min. bending radius	guided bending: R = 65mm	
(according to DIN EN 61386-24)	free bending: R = 10 x speedpipe-outer diameter	
Transport and storage temperatures	-40 to +70	°C
Laying or assembly temperature	-10 to +50	°C
	-40 to +70	°C
Operating temperature	Temperature at which the full functionality of the installed or laid components is given	
UV resistance (DIN EN ISO 4892-1)	3 years (south-european climate)	
For installation follow the installation	on instruction and the laying instruction!	
	Technical data	
Quality	Value	Unit
	Material	
Material	PolyEthylen PE-HD, regenerate- and recyclate-free	
MFI (according to DIN 8075)	max. 30	%
Homogeneity	free from inclusions < 0.02	mm <sup>2</sup>
Internal pressure creep rupture test (DIN 16874)	Sigma 4.0 for 170h at 80°C	N/mm <sup>2</sup>
Fire behavior (DIN EN 13501-1)	E	
	speedpipe-ground 20x2.5	
Dimension	$D = 20.0^{+0.15}$ ; s = 2.5 <sup>+0.1</sup>	mm
Colour of stripes	pink opposite transparent windows	
Pressure nominal	PN 10	
Inner surface	90 optimized sliding ribs	
Burst pressure	min. 40	bar at 20°C
Max. recommended tensile strength	1300	N at 20°C
Tensile strength at break	1900	N at 20°C

to DIN EN 61386-24) gabocom is certified by the quality system following DIN EN ISO 9001, the environmental management system DIN EN ISO 14001 and the

2000

energy management system DIN EN 50001. The used materials meet the Reach default (EU regulation 1907/2006)

and the RoHS default (EU guidelines 2011/65).

· · ·	•	
gabo Systemtechnik GmbH	Tel. +49 9962 950-200	Editor: AF
Am Schaidweg 7	Fax +49 9962 950-202	Release: MK
94559 Niederwinkling	info@gabocom.com	Date: 31.05.2021
GERMANY	www.gabocom.com	Edition: 4

No responsibility is taken for the currency and completeness of details and information. This document can be revised and supplemented without prior notice. Liability for damages is excluded.

© 2021 gabo Systemtechnik GmbH, all rights reserved

Apex pressure (according

N at 20°C