

speed•pipe[®]-ground 14x2.0 **€**



General data		
ltem	speedpipe-ground 14x2.0	
Description	speedpipe-ground for the direct bury	
Production length on spool (1200x370mm)	1500m	
Weight	approx. 0.074 kg/m	
Total weight	approx. 140 kg (including spool)	
Min. bending radius	guided bending: R = 65mm	
(according to DIN EN 61386-24)	free bending: R = 10 x speedpipe-outer diameter	
Transport and storage temperatures	-40 to +70	°C
Laying or assembly temperature	-10 to +50	°C
	-40 to +70	°C
Operating temperature	Temperature at which the full functionality of the installed or laid components is given	
UV resistance (DIN EN ISO 4892-1)	3 years (south-european climate)	
For installation follow the installation instruction and the laying instruction!		
Technical data		
Quality	Value	Unit
Material		
Material	PolyEthylen PE-HD, regenerate- and recyclat	te-free
MFI (according to DIN 8075)	max. 30	%
Homogeneity	free from inclusions < 0.02	mm ²
Internal pressure creep rupture test (DIN 16874)	Sigma 4.0 for 170h at 80°C	N/mm ²
Fire behavior (DIN EN 13501-1) E		
speedpipe-ground 14x2.0		
Dimension	$D = 14.0^{+0.1}$; s = 2.0 ^{+0.15}	mm
Colour of stripes	orange opposite transparent windows	
Pressure nominal	PN 16	
Inner surface	60 optimized sliding ribs	
Burst pressure	min. 50	bar at 20°C
Max. recommended tensile strength	800	N at 20°C
Tensile strength at break	1200	N at 20°C
Apex pressure (according to DIN EN 61386-24)	2000	N at 20°C
gabocom is certified by the quality system following DIN EN ISO 9001,		
the environmental management system DIN EN ISO 14001 and the		
energy management system DIN EN 50001.		
The used materials meet the Reach default (EU regulation 1907/2006)		
and the BoHS default (FU quidelines 2011/65)		
aabo Systemtechnik GmbH	Tel. +49 9962 950-200	Editor: AF
Am Schaidweg 7	Fax +49 9962 950-202	Release: MK
94559 Niederwinkling GERMANY	info@gabocom.com www.gabocom.com	Date: 16.12.2020 Edition: 4

No responsibility is taken for the currency and completeness of details and information. This document can be revised and supplemented without prior notice. Liability for damages is excluded.