


Loose Tube Fibre Optic Indoor/Outdoor Cable

8 Element All Dielectric Dry Core Design

MiDia[®] SAFE



Issue May 2017
according to **OFS Generic Specification**



Application

Mainly used in outside plant to building transitions and inter-building installations

Design

- Optical Fibres
- Gel-filled Buffer Tubes
- Non-metallic Central Member
- Water Blocking Material
- Non-Metallic Strength Elements
- Ripcords
- Flame Retardant Jacket

Features

- All Dielectric Cable
- Dry Core Design – Cable core water blocked by means of dry “water swellable” technology - for quicker, cleaner cable prep for jointing
- Individual coloured tubes
- Low smoke/zero halogen (LSOH) rated
- Meets the requirements of IEC 61034-2, IEC 60332-1-2 and EN 50399
- Meets CPR Euro Class E_{ca} according EN 13501/ 6

Version illustrated is the 96 Fibre Cable

Fibre Count	Tubes	Core Design	Outer Diameter [mm]	Cable Weight [kg/km]	Standard Length [m]	AT-Code*
12 Fibres per tube						
96	8	1+8	10	105	2000 / 4000 / 6000 / 8000	AT-[][][]16HT-096

This table shows nominal diameter and weight values which may differ in shipments.
Fillers are natural coloured. *Please refer to the OFS AT- Code. The blanks specify the fibre type.

Identification

Tube and Fibre Colour Code:

1	Blue	2	Orange	3	Green	4	Brown	5	Grey	6	White
7	Red	8	Black	9	Yellow	10	Violet	11	Rose	12	Aqua

Alternative tube and fibre colour code available on request

Sheath Marking

OFS OPTICAL CABLE MIDIA SAFE [ID] [MM/YYYY] [Handset Sign] xxxF [Meter Marking]

Alternative sheath printing available on request.

Loose Tube Fibre Optic Indoor/Outdoor Cable

8 Element All Dielectric Dry Core Design

MiDia[®] SAFE



Issue May 2017
according to **OFS Generic Specification**

Mechanical Properties and Environmental Behaviour

Tests according to IEC 60794

	Parameter	Requirement	Value
Tensile Performance: IEC 60794-1-21-E1A and E1B	Long term load	- No attenuation increase* - No fibre strain	Load: 500 N
	Short term load, during installation	- No changes in attenuation before versus after load - Max. fibre strain 0.5%	Load: 2.0 x W <i>W is the weight of the cable</i>
Crush Performance: IEC 60794-1-21-E3A	Long term load	- No attenuation increase*	Load (Plate / Plate): 500 N
	Short term load	- No changes in attenuation before versus after load - No damage**	Load (Plate / Plate): 1500 N
Bending Performance: IEC 60794-1-21-E11	Handling fixed installed	- No attenuation increase*	Bend radius: 100 mm
	During installation (under load)	- No changes in attenuation before versus after load	Bend radius: 200 mm
Temperatures: IEC 60794-1-22-F1	Operation	- No attenuation increase*	-40 to +70°C
	Installation		-15 to +60°C
	Storage/Shipping		-40 to +70°C

*No changes in attenuation means that any changes in measurement value, either positive or negative within the uncertainty of measurement shall be ignored. The total uncertainty of measurement shall be less than or equal to 0.05 dB.

**Mechanical damage – when examined visually without magnification, there shall be no evidence of damage to the sheath. The imprint of plates will not be considered as damage.

Shipping Information

Cable Length	Drum Dimensions (approx.)		Shipping Weight (calc.)	
	Diameter(battened)	Width	Without lagging	With lagging
2000 m	1050 mm	790 mm	270 kg	290 kg
4000 m	1250 mm	790 mm	500 kg	540 kg
6000 m	1450 mm	790 mm	740 kg	780 kg
8000 m	1600 mm	1055 mm	970 kg	1030 kg

The shipping information are given for one-way reels. Reusable reels are available on request.

OFS reserves the right to improve, enhance and modify the features and specifications of OFS products without prior notification.

Please ensure you have the latest version of the data sheet.

For additional information please contact your sales representative.

You can also visit our

website at <http://www.ofsoptics.com>.

Telephone: +49 (0) 228 7489 201

Email: cableinfo@ofsoptics.com

This data sheet is property of OFS.



AllWave[®] + Fibre

Zero Water Peak



ofs

A Furukawa Company

The industry's first zero water peak single-mode fibre for reliable full-spectrum performance + enhanced bend performance.

Overview

AllWave[®]+ Zero Water Peak (ZWP) Single-Mode Optical Fibre improves performance for optical transmission systems operating over any part of the entire wavelength range from 1260 nm to 1625 nm compared with conventional single-mode fibre. AllWave+ Fibre offers the exceptional performance of our AllWave Fibre specifications along with a 40% smaller minimum bend radius, a 50% lower bend loss and a 33% improved polarization mode dispersion (PMD) link design value. AllWave+ Fibre intermixes seamlessly with the installed base of single-mode fibres with a nominal mode field diameter of 9.2 μm .

Product Description


AllWave+ Fibre is a combination ITU-T G.652.D and G.657.A1 compliant fibre ideally designed for use in backhaul, metropolitan, and FTTX networks. Developed and manufactured by OFS, AllWave+ Fibre provides low and stable loss performance in the 1360 – 1460 nm E-band; plus it offers reduced bending loss to improve performance for applications operating in the bend-sensitive 1460 – 1625 nm S, C, and L bands. Its bending performance is far superior to the G.652.D Recommendation and compliant to the G.657.A1 Recommendation, supporting a minimum bend radius of 10 mm and lower bend loss than conventional single-mode fibres. This low bending loss provides improved performance and service reliability and helps to reduce the size of cables and terminals for lower cost installations. AllWave+ Fibre also has the same 9.2 micron mode field (light carrying) diameter of the installed base of single-mode fibres, such as AllWave Fibre, which enables seamless splicing, testing, and faster network turn-up.

With a composition of high purity synthetic silica throughout both the core and cladding, AllWave+ Fibre has stable and permanent low loss and mechanical reliability. OFS' patented ZWP fibre manufacturing process, which eliminates the hydrogen-aging defects, provides a 50% increase in usable spectrum compared to G.652.A and G.652.B fibre. What's more, its ultra-low PMD enables speed and distance upgrades. AllWave+ Fibre offers dramatically improved performance in almost every characteristic over conventional single-mode fibre and is fully backward compatible to any G.652 compliant single-mode fibre.

Features/Benefits:

- Low optical loss across the entire spectrum from 1260 – 1625 nm
- Lower bending loss for improved performance and service reliability, and to help reduce the size of cables and terminals
- A 9.2 micron nominal mode field diameter to facilitate splicing and testing
- Geometric control at the industry's tightest level for ultra-low splice loss and improved connector performance
- Low, stable loss performance in the 1360 – 1460 nm E-band, enabling 16-channel CWDM, DWDM, and FTTX support on a single fibre
- Comprised of high purity synthetic silica for long-term attenuation stability and mechanical reliability
- Ultra-low fibre PMD allows for speed and distance upgrades

Compatible with Conventional Single-Mode Fibre, but with More Available Spectrum



AllWave ZWP Fibre has lower & stable loss throughout by removing the water peak defect

AllWave ZWP Fibre has over 100 nm MORE spectrum

AllWave ZWP Fibre provides up to 22.5% lower attenuation and longer range compared to "enhanced" or Low Water Peak (LWP) fibres

Applications

AllWave+ Fibre provides outstanding cable performance and design freedom for fibre management systems in:

- FTTX
- Local access
- Mobile backhaul
- Metro access
- Metro edge
- Campus backbones
- Long haul

North America

Telephone: 508-347-8590
Toll Free: 800-799-7732
Fax: 508-347-1211
E-mail: fibersalesnar@ofsoptics.com

Asia Pacific

Telephone: +852 2836 7102
Fax: +86 21 5295 1949
E-mail: fibersalesap@ofsoptics.com

Caribbean, Latin America

Telephone: +1-508-347-8590
Fax: +1-508-347-1211
E-mail: fibersalescala@ofsoptics.com

Japan

Telephone: +81-3-3286-3424
Fax: +81-3-3286-3708 or 3190
E-mail: fibersalesjapan@ofsoptics.com

Europe, Middle East, Africa

Telephone: +45-43 48 3736
Fax: +45 4348 3444
E-mail: ofssalesdk@ofsoptics.com

China

Telephone: +86 147 154 93629
Fax: +86 10 65059515
E-mail: fibersaleschina@ofsoptics.com

For additional information please contact your sales representative.

You can also visit our website at: www.ofsoptics.com/ofs-fiber or call 1-888-fiberhelp (from inside the USA).

For regional assistance, contact the global location closest to you.



A Furukawa Company



AllWave is a registered trademark of OFS Fitel, LLC.

OFS reserves the right to make changes to the prices and product(s) described in this document at any time without notice. This document is for informational purposes only and is not intended to modify or supplement any OFS warranties or specifications relating to any of its products or services.

Copyright © 2014 OFS Fitel, LLC.
All rights reserved, printed in USA.
OFS Marketing Communications
Use electronic files, available at: www.ofsoptics.com
Use less paper



Doc ID: fiber-159-A4 Publish Date: 0214

Product Specifications

Physical Characteristics

Clad Diameter	125.0 ± 0.7 µm
Clad Non-Circularity	≤ 0.7 %
Core/Clad Concentricity Error (Offset)	≤ 0.5 µm, < 0.2 µm typically
Coating Diameter (Natural)	235 - 245 µm
Coating-Clad Concentricity Error (Offset)	≤ 12 µm
Tensile Proof Test (<i>Other proof test levels available on request</i>)	100 kpsi (0.69 GPa)
Coating Strip Force	Range: 1.0 N ≤ CSF ≤ 9.0 N
Standard Reel Lengths	Up to 50.4 km (31.3 miles)

Optical Characteristics

Attenuation	Maximum	Typical
at 1310 nm	≤ 0.34 dB/km	≤ 0.32 dB/km
at 1385 nm	≤ 0.31 dB/km	≤ 0.28 dB/km
at 1490 nm	≤ 0.24 dB/km	≤ 0.21 dB/km
at 1550 nm	≤ 0.21 dB/km	≤ 0.19 dB/km
at 1625 nm	≤ 0.24 dB/km	≤ 0.20 dB/km

Attenuation vs. Wavelength

Range (nm)	Reference (nm) λ	α
1285 – 1330	1310	0.03
1360 – 1480	1385	0.04
1525 – 1575	1550	0.02
1460 – 1625	1550	0.04

The attenuation in a given wavelength range does not exceed the attenuation of the reference wavelength (λ) by more than the value α.

Attenuation Uniformity / Point Discontinuities at 1310 nm and 1550 nm	≤ 0.05 dB
---	-----------

Macrobending Attenuation:

The maximum attenuation with bending does not exceed the specified values under the following deployment conditions:

Deployment Condition	Wavelength	Induced Attenuation
1 turn on a 10 mm radius mandrel	1550 nm	≤ 0.75 dB
	1625 nm	≤ 1.50 dB
10 turns on a 15 mm radius mandrel	1550 nm	≤ 0.25 dB
	1625 nm	≤ 1.00 dB
100 turns on a 30 mm radius mandrel	1550 nm	≤ 0.03 dB
	1625 nm	≤ 0.03 dB

Chromatic Dispersion

Zero Dispersion Wavelength (λ ₀)	1300 – 1322 nm
Zero Dispersion Slope (S ₀)	≤ 0.090 ps/nm ² -km
Typical Dispersion Slope	0.087 ps/nm ² -km

Group Refractive Index

at 1310 nm	1.467
at 1550 nm	1.468

Mode Field Diameter

at 1310 nm	9.2 ± 0.4 µm
at 1550 nm	10.4 ± 0.5 µm

Cut-off Wavelength (λ _{cc})	≤ 1260 nm
---------------------------------------	-----------

Polarization Mode Dispersion (PMD)¹

Fibre PMD Link Design Value (LDV) ²	< 0.04 ps/√km
Maximum Individual Fibre	< 0.1 ps/√km
Typical Fibre LMC PMD	< 0.02 ps/√km

¹ As measured with low mode coupling (LMC) technique in fibre form, value may change when cabled. Check with your cable manufacturer for specific PMD limits in cable form.

² The PMD Link Design Value complies with IEC 60794-3, September 2001 (N = 20, Q = 0.01%). Details are described in IEC 61282-3 TR Ed 2, October 2006.

Environmental Characteristics (at 1310, 1550 & 1625 nm)

Temperature Cycling (-60° + 85° C)	≤ 0.05 dB/km
High Temperature Aging (85 ± 2° C)	≤ 0.05 dB/km
Temperature & Humidity Cycling (at -10° C to +85° C and 85 to ~98% RH)	≤ 0.05 dB/km
Water Immersion (23 ± 2° C)	≤ 0.05 dB/km