


All-Dielectric, Self Supporting (ADSS) Aerial Loose Tube Fiber Optic Cable

Dry core design

PowerGuide^{®200} SkyLight



Issue May 2018
according to **OFS Generic Specification**



Application

Optimized for Aerial- and Duct Installation with fiber counts up to 288 fibers

Design

- Optical fibers
- Gel-filled buffer tubes
- Non-metallic central member
- Water blocking threads
- Non-metallic aramid strength elements
- Ripcords
- Outer HDPE-jacket

Benefits

- Excellent, cost- effective option for short aerial cable spans
- Outstanding optical performance, durability and field reliability
- Fast, one-step installation for valuable time and cost savings
- Small cable diameter and bend radius for easy deployment in aerial- to- underground installation
- Easily strippable sheath for quick, convenient cable preparation

Version illustrated is the 288 Fiber 12 Element Cable

Fibre Count	Tubes	Core Design	Outer Diameter [mm]	Cable Weight [kg/km]	AT-Code**
264	11 (24F)	1+12 (1 Filler*)	15.0	180	AT-[][][17UF-264-CNAB
288	12 (24F)	1+12	15.0	180	AT-[][][17UF-288-CNAB

This table shows nominal diameter and weight values which may differ in shipments.

*Fillers are natural colored

**Please refer to the OFS AT- Code. The blanks specify the fiber type.

Identification

Tube Color Code:

1	Blue	2	Orange	3	Green	4	Brown	5	Grey	6	White
7	Red	8	Black	9	Yellow	10	Violet	11	Rose	12	Aqua

Fiber Color Code:

1	Blue	2	Orange	3	Green	4	Brown	5	Grey	6	White
7	Red	8	Black	9	Yellow	10	Violet	11	Rose	12	Aqua
13	Blue*	14	Orange*	15	Green*	16	Brown*	17	Grey*	18	White*
19	Red*	20	Nature	21	Yellow*	22	Violet*	23	Rose*	24	Aqua*

* Black ring

Alternative tube and fiber color code available on request.

All-Dielectric, Self Supporting (ADSS) Aerial Loose Tube Fiber Optic Cable

Dry core design

PowerGuide^{®200} SkyLight



Issue May 2018
according to **OFS Generic Specification**

Sheath Marking:

OFS OPTICAL ADSS CABLE [ID] [MM/YYYY] [Handset Sign] xxxF [Meter Marking]

Alternative sheath printing available on request.

In case of order the exact sheath printing text will be clarified with the customer.

Shipping Information

Cable Length	Drum Dimensions (approx.)		Shipping Weight (calc.)	
	Diameter(battened)	Width	Without lagging	With lagging
2 Km	1450 mm	790 mm	470 kg	510 kg
4 Km	1600 mm	1055 mm	850 kg	910 kg
6 Km	1750 mm	1055 mm	1230 kg	1290 kg
8 Km	2050 mm	1100 mm	1620 kg	1700 kg

The shipping information are given for one-way reels. Reusable reels are available on request.

Temperatures

IEC 60794-1-22-F1	Operation	-40°C to +70°C
	Installation	-15°C to +60°C
	Storage/Shipping	-40°C to +70°C

Sag and Tension Calculation

AT-[][]17UF-288-CNAB

NESC Heavy Loading Conditions

Ice Thickness	12,7 mm
Wind Pressure	19,53 kg/m ² (60 km/h)
Low Temperature	- 17,8 °C
Safety Factor	0.45 kg/m

Tension @ Maximum Span for 1,0 % Installation Sag

Short Term	6600 N
Long Term	1550 N

Maximum Span	70 m
Cable Weight	180 kg/km
Cable Diameter	15.0 mm
Installation Temperature	23 °C
Cable Modulus	794.8 kg/mm ²
CTE (C ⁻¹)	1.57E- 05

All-Dielectric, Self Supporting (ADSS) Aerial Loose Tube Fiber Optic Cable

Dry core design

PowerGuide^{®200} SkyLight



Issue May 2018
according to **OFS Generic Specification**

Recommended hardware for spans up to 150m

Dead End Assembly:

PLP FIBERLIGN[®] Dielectric Dead-end for ADSS,
2872007C1E1 , Max. Tension: 2500 lbs. (1135 kg)

Fixed Tangent Support:

PLP FIBERLIGN[®] Aluminum Support for ADSS, 4450102

Suspended Support:

PLP FIBERLIGN[®] Aluminum Suspension for ADSS, 4450202

Slack Storage Devices:

FIBERLIGN[®] In-Span Storage System, FIS12A

Down Lead Cushion:

FIBERLIGN[®] Downlead Cushion for ADSS,
8003043

Vibration Dampers:

FIBERLIGN[®] Dielectric Damper for ADSS Cable,
50509862

Pertinent installation information

Maximum rated cable load (MRCL)	6,6 kN
Bending Performance: (IEC 60794-1-21-E11)	
Handling fixed installed - No attenuation increase*	Bend radius: 150 mm
During installation (under Load) - No changes in attenuation before versus after load	Bend radius: 300 mm

*No changes in attenuation means that any changes in measurement value, either positive or negative within the uncertainty of measurement shall be ignored. The total uncertainty of measurement shall be less than or equal to 0.05 dB.

When to use hardware

Dead End Assembly

- Used whenever a cable should not slip
 - Cable start and end points
 - Where line angles exceed 20°
 - Road, river, railroad crossings
 - Closure locations
- Different types available dependent upon cable design and application
- Most attachment hardware is used with 5/8" pole line hardware




Tangent and Suspension Supports

- Typically used in small line angle (<20°, depending on type) situations
- Provides vertical support, not designed to support cable tension
- Multiple types depending span length and application
- Allows cable slippage during imbalanced load situations



Vibration Dampers

- ADSS cables can experience Aeolian vibration under certain circumstances
- Circumstances conducive to Aeolian vibration
- Laminar wind flow, Wide open spaces, Light winds, High tensions
- Vibration dampers minimize the effects of this vibration



Installation document references

IP 014 PowerGuide[®] Installation

IP 014A PowerGuide[®] ADSS CABLE Installation Guideline Distribution Line Applications

IP 006 PowerGuide[®] Sheath Removal

IP 017 PowerGuide[®] Hardware Installation

AN-101 Maximum Rated Cable Loads & Minimum Bending Diameter

AN-203 Space Potential Calculation for PowerGuide[®] ADSS Cable

Installation documents available upon request.

All-Dielectric, Self Supporting (ADSS) Aerial Loose Tube Fiber Optic Cable

Dry core design

PowerGuide^{®200} SkyLight



Issue May 2018
according to **OFS Generic Specification**

PowerGuide SkyLight Cable Ordering Information

Example: **AT-8EE17UF-NNN¹-CMCB**

Fiber ² Sheath Core Fiber Count Custom ³					
Part Number: AT-S1 S2 SF S3 S4 S5 S6 - NNN - CMCB					
S1= Fiber Selection 8= 1310/1550 nm (AllWave [®] FLEX 200µm ZWP Fiber) 9= 1310/1550 nm (AllWave [®] FLEX + 200µm ZWP Fiber)		S2= Fiber Transmission Performance E= 0.36/0.31/0.27/0.25/0.27 dB/km @ 1310/1385/1490/1550/1625 nm (AllWave [®] FLEX 200µm ZWP Fiber) (AllWave [®] FLEX + 200µm ZWP Fiber)		SF= Fiber Type E= AllWave [®] ZWP Single Mode S3= Sheath Construction 1= All-Dielectric single jacket S4= Tensile Load 7= ADSS	
S5= Core Type U= Dry Core Loose Tube		S6= Fibers per Tube F= 24 Fibers		NNN= Fiber Count	

¹ Part Number shown is for PowerGuide ADSS Cable with 200 µm Single Mode AllWave[®]FLEX 200µm ZWP Fiber with maximum attenuation: 0.36/0.31/0.27/0.25/0.27 dB/km @ 1310/1385/1490/1550/1625 nm .

² Contact OFS sales representative for information on other cable variations, including additional fiber types, composite cables and attenuation.

³ Consult with us regarding your application, span lengths and loading conditions to complete the custom design and part number of your complete sheath strengths system.

The information is believed to be accurate at time of issue.

OFS reserves the right to improve, enhance and modify the features and specifications of OFS products without prior notification.

Please ensure you have the latest version of the data sheet.

This data sheet is property of OFS.

For additional information please contact your sales representative.

You can also visit our website at <http://www.ofsoptics.com>.

Telephone: +49 (0) 228 7489 201

Email: [cableinfo@ofsoptics.com](mailto: cableinfo@ofsoptics.com)






A Furukawa Company

AllWave® FLEX 200 μ m Fiber

Reliable Bend-Optimized Performance for Smaller Diameter, Higher Density Cable Applications



Features and Benefits

- Bend optimized design for tight, low loss bends without risking fiber strength and long-term reliability
- 36% less area than conventional 250 μ m coated fiber enabling smaller diameter cables and a greater number of fibers per tube
- Ideally suited for high fiber count cables and microcables where cable diameter needs to be minimized
- Zero Water Peak fiber provides a 50% increase in usable optical spectrum, enabling 16-channel CWDM and DWDM support
- Proof-tested to 100 kpsi to improve long term reliability and simplify cabling
- Ultra-low Polarization Mode Dispersion (PMD) enables speed and distance upgrades

Applications

- FTTx
- High count fiber cables
- High power applications
- Microcables
- Closures
- At the customer premises
- Any application with transmission speeds of 40 Gb/s and beyond

Overview

OFS offers AllWave FLEX Bend-Optimized Single-Mode Optical Fiber with a 200 μ m coating diameter for use in cables with higher fiber counts per tube and in microcables where cable diameters must be minimized. The fibers offer all the other performance advantages and 30-year reliability of standard AllWave FLEX products.

Product Description

AllWave FLEX 200 μ m Optical Fiber supports higher density and lower diameter cables, providing outstanding macrobend and microbend performance for Access, Fiber-to-the-Home (FTTH), enterprise networks, or any application where small bend diameters may be encountered. This G.657.A1 fiber maintains very low bending loss across the full usable spectrum of wavelengths from 1260 to 1625 nm. It can be coiled into a 20 mm diameter loop with < 0.5 dB incurred loss at 1625 nm and < 0.2 dB incurred loss at 1550 nm – five times better bending performance than conventional single-mode and leading LWP fibers.

Outstanding Macrobend Performance

- **100 turns on a 25 mm radius mandrel**
< 0.01 dB @ 1550 nm
< 0.05 dB @ 1625 nm
- **10 turns on a 15 mm radius mandrel**
< 0.2 dB @ 1550 nm
< 0.5 dB @ 1625 nm
- **1 turn on a 10 mm radius mandrel**
< 0.2 dB @ 1550 nm
< 0.5 dB @ 1625 nm

For additional information please contact your sales representative.

You can also visit our website at www.ofsoptics.com or call **1-888-fiberhelp** (1-888-342-3743) USA or **1-770-798-5555** outside the USA.

North America

Telephone: 508-347-8590
Toll Free: 800-799-7732
Fax: 508-347-1211
E-mail: fibersalesnar@ofsoptics.com

Asia Pacific

Telephone: +852 2506 5054
Fax: +852 2506 0166
E-mail: fibersalesap@ofsoptics.com

Caribbean, Latin America

Telephone: +1-508-347-8590
Fax: +1-508-347-1211
E-mail: fibersalescala@ofsoptics.com

Japan

Telephone: +81-3-3286-3424
Fax: +81-3-3286-3708 or 3190
E-mail: fibersalesjapan@ofsoptics.com

Europe, Middle East, Africa

Telephone: +45-43 48 3736
Fax: +45 4348 3444
E-mail: ofssalesdk@ofsoptics.com

China

Telephone: +86 10 6505 3660
Fax: +86 10 65059515
E-mail: fibersaleschina@ofsoptics.com



Copyright © 2017 OFS Fitel, LLC.
All rights reserved, printed in USA.

OFS Marketing Communications
Doc ID: fiber-146
Date: 0917

AllWave is a registered trademark of OFS Fitel, LLC.

OFS reserves the right to make changes to the prices and product(s) described in this document at any time without notice. This document is for informational purposes only and is not intended to modify or supplement any OFS warranties or specifications relating to any of its products or services.

200 μ m AllWave® FLEX Fiber

Product Specifications		200 μm AllWave FLEX Fiber	
Physical Characteristics			
Clad Diameter		125.0 ± 0.7 μm	
Clad Non-Circularity		≤ 1 %	
Core/Clad Concentricity Error (Offset)		≤ 0.5 μm, < 0.2 μm typically	
Coating Diameter	(Uncolored) (Colored)	190 ± 10 μm 200 ± 10 μm	
Coating-Clad Concentricity Error (Offset)		≤ 12 μm	
Tensile Proof Test (Other proof test levels available on request)		100 kpsi (0.69 GPa)	
Coating Strip Force		Range: ≥ 0.5 N < 8.9 N	
Standard Reel Lengths		50.4 km	
Optical Characteristics			
Attenuation		Maximum	Typical
at 1310 nm		≤ 0.35 dB/km	≤ 0.34 dB/km
at 1385 nm		≤ 0.31 dB/km	≤ 0.28 dB/km
at 1490 nm		≤ 0.24 dB/km	≤ 0.21 dB/km
at 1550 nm		≤ 0.21 dB/km	≤ 0.19 dB/km
at 1625 nm		≤ 0.24 dB/km	≤ 0.20 dB/km
Attenuation vs. Wavelength Range (nm)		Reference (nm) λ	α
1285 – 1330		1310	0.03
1360 – 1480		1385	0.04
1525 – 1575		1550	0.02
1460 – 1625		1550	0.04
*The attenuation in a given wavelength range does not exceed the attenuation of the reference wavelength (λ) by more than the value α.			
Attenuation Uniformity / Point Discontinuities at 1310 nm and 1550 nm		≤ 0.05 dB	
Chromatic Dispersion			
Zero Dispersion Wavelength (λ ₀)		1302 – 1322 nm	
Zero Dispersion Slope (S ₀)		≤ 0.092 ps/nm ² -km	
Typical Dispersion Slope		0.088 ps/nm ² -km	
Group Refractive Index			
at 1310 nm		1.467	
at 1550 nm		1.468	
Mode Field Diameter			
at 1310 nm		8.5 - 9.3 μm	
at 1550 nm		9.4 - 10.4 μm (typical)	
Cut-off Wavelength (λ _{cc})		≤ 1260 nm	
Polarization Mode Dispersion (PMD) ¹			
Fiber PMD Link Design Value (LDV) ²		≤ 0.06 ps/√km	
Maximum Individual Fiber		≤ 0.1 ps/√km	
Typical Fiber LMC PMD		≤ 0.02 ps/√km	
¹ As measured with low mode coupling (LMC) technique in fiber form, value may change when cabled. Check with your cable manufacturer for specific PMD limits in cable form.			
² The PMD Link Design Value complies with IEC 60794-3, September 2001 (N = 20, Q = 0.01%). Details are described in IEC 61282-3 TR Ed 2, October 2006.			
Environmental Characteristics (at 1310, 1550 & 1625 nm)			
Temperature Cycling (-60° + 85 °C)		≤ 0.05 dB/km	
High Temperature Aging (85 ± 2 °C)		≤ 0.05 dB/km	
Temperature & Humidity Cycling (at -10 °C to +85 °C and 95% RH)		≤ 0.05 dB/km	
Water Immersion (23 ± 2 °C)		≤ 0.05 dB/km	