


Technical datasheet for:

SRV-G 40 / 3x16 C€



| General data | | | | |
|--|---|---|--|--|
| Item | speedpipe-bundle-ground SRV-G 40 / 3x16 | | | |
| Description | speedpipe-bundle for pulling into existing ducts, filled with 3 pieces of speedpipe-ground 16x2.0 | | | |
| Production length on spool (2400x1200mm) | 2100m | | | |
| Weight | approx. 0.34 kg/m | | | |
| Total weight | approx. 1100 kg (including spool) | | | |
| Recommend bending radius | > 2.5m | every small bending radius reduce the blow in length of the cable | | |
| Min. bending radius | 1.0m | | | |
| Max. recommended tensile strength | 3100 N (at 20°C) | Ensure uniform force distribution! | | |
| Tensile strength at break | 3900 N (at 20°C) | | | |


| Technical data | | | | |
|--|-------------------------------------|-------------------|--|--|
| Quality | Value | Unit | | |
| Material Material | | | | |
| Material | PolyEthylen PE | | | |
| MFI (according to DIN 8075) | max. 30 | % | | |
| Homogeneity | free from inclusions < 0.02 | mm ² | | |
| Internal pressure creep rupture test (DIN 16874) | Sigma 4.0 for 170h at 80°C | N/mm ² | | |
| Fire behavior (DIN EN 13501-1) | E | | | |
| Jacket pipe | | | | |
| Dimension | $D = 40.0^{+0.4}; s = 0.5^{+0.2}$ | mm | | |
| Colour | orange | | | |
| Pressure nominal | based on wall thickness bigger PN 1 | | | |
| Burst pressure | > 3 | bar at 20°C | | |
| Max. recommended tensile strength | 550 | N at 20°C | | |
| Tensile strength at break | 800 | N at 20°C | | |

No responsibility is taken for the currency and completeness of details and information. This document can be revised and supplemented without prior notice. Liability for damages is excluded.



Technical datasheet for:

SRV-G 40 / 3x16 C€



| Technical data | | | | |
|--|---|-------------|--|--|
| Quality | Value | Unit | | |
| speedpipe-ground 16x2.0 | | | | |
| Dimension | $D = 16.0^{+0.15}$; $s = 2.0^{+0.1}$ | mm | | |
| Colour of stripes | black, brown and red opposite transparent windows | | | |
| Pressure nominal | based on wall thickness bigger PN 10 | | | |
| Inner surface | 79 optimized sliding ribs | | | |
| Burst pressure | min. 45 | bar at 20°C | | |
| Max. recommended tensile strength | 900 | N at 20°C | | |
| Tensile strength at break | 1400 | N at 20°C | | |
| Apex pressure (according to DIN EN 61386-24) | 1700 | N at 20°C | | |

Colour code

| 1) black | |
|----------|--|
| 2) brown | |
| 3) red | |

gabocom is certified by the quality system following DIN EN ISO 9001, the environmental management system DIN EN ISO 14001 and the energy management system DIN EN 50001.

The weed materials most the REACH default (ELI regulation 1907/2006)

The used materials meet the REACH default (EU regulation 1907/2006) and the RoHS default (EU guidelines 2011/65).

gabo Systemtechnik GmbH Am Schaidweg 7 94559 Niederwinkling GERMANY Tel. +49 9962 950-200 Fax +49 9962 950-202 info@gabocom.com www.gabocom.com Editor: LF Release: MK Date: 16.12.2015

Edition: 3

No responsibility is taken for the currency and completeness of details and information. This document can be revised and supplemented without prior notice. Liability for damages is excluded.