

## MICRODUCTS

# MicroDucts LSHF 16/12 mm

MicroDucts LSHF (Low Smoke Halogen Free) are specifically designed for in-building applications where fire, smoke, and toxic fumes may pose a risk to human life and critical electronic equipment. Tested to stringent European standards, MicroDucts LSHF offer best-in-class fire performance when tested to EN 13501-1. Once installed, they enable seamless, cost-effective moves, adds, and changes (MACs) and end-to-end fibre jetting in indoor FTTH, LAN, data centre, and transportation networks.

- Made from quality flame retardant materials, formulated for long life expectancy
- Tested in accordance with EN 13501-1 for reaction to fire and achieved best-in-class fire performance and smoke generation rating 'B s1 d0' when mounted on gypsum plasterboard
- Halogen free, tested in accordance with EN 50642
- MicroDucts LSHF are tested by respected German test institute VDE and marked in accordance with EN IEC 61386-22 (VDE 0605-22):2021-12; EN IEC 61386-22:2021+A11:2021. Production is regularly audited by VDE.
- Available with SILICORE®, a permanently lubricated, coextruded inner lining that provides a lower inner coefficient of friction (<0.1) for maximum cable blowing length
- Available in natural, milky white color
- Designed for a fill ratio between a minimum of 50% and a maximum of 75%
- 

## COLORS



Note: If a pre-installed rope is utilised, it should be removed upon completion of the installation.



## DETAILS

- Footage/Meter Markings


## OPTIONS

- Internal Ribs
- Smooth Interior Wall
- Pre-installed Rope

TECHNICAL SPECIFICATIONS

Product Description	MicroDucts LSHF 16/12 mm
---------------------	--------------------------

TECHNICAL DETAILS	
Bend Radius	160 mm
Outside Diameter (B)	16 mm
OD Tolerance +	0.1 mm
OD Tolerance -	0.1 mm
Inside Diameter (C)	12 mm
Wall Thickness (A)	2 mm
Wall Tolerance +	0.1 mm
Wall Tolerance -	0.1 mm
MicroDuct Size (OD/ID)	16/12 mm



PHYSICAL PROPERTIES

GENERAL PRODUCT INFORMATION	
Storage Temperature	-15 to 60°C
InstallationTemperature	-5 to 50°C
Use Temperature	-5 to 60°C
Interior wall	Smooth,Ribbed
Pre-Lubrication Class	Silicore
UV Stability (Years)	0

PERFORMANCE PROPERTIES	
Burst pressure (bar)	25
Maximum Pulling Force - Test Method: ISO 527-1, 2	800 N
Blown ball test (BB test) - Test Method: EN ISO 1167-1, 2	Pass, with minimum ball diameter of 80% of ID
Friction Coefficient - Test Method: IEC/TR 62470 method A	max. 0.1
Burst pressure Test Method	EN ISO 1167-1, 2
Resistance of Marking	IEC 60794-1-2, Method E2B, technique no 2
Longitudinal reversion - Test Method: EN ISO 2505	max 3 %

PACKAGING	
Nominal Weight of Conduit	87 kg/km
Duct Ovality Pre-Winding - Test Method: EN ISO 3126	5 %
Length on Drum	1250 m
Drum Dimensions	120x46x36 cm
Ovality Test Method	EN ISO 3126
Print Marking	0000 m - Dura-Line - LOT No 12345678 - MicroDucts LSHF - Ribbed/Smooth - 16/12 - VDE-REG F179 3-3-2-1-2-0-0-0-0-0-1-0-0-1 - Silicore (optional) - Production date <YYYY/MM/DD>

CLASSIFICATION	
Classification Code DIN EN 61386-22 (VDE 0605 Teil22)	3-3-2-1-2-0-0-0-0-0-1-0-0-1

