

Technical datasheet for:



General data			
Item	speedpipe-ground 7x1.5		
Description	speedpipe-ground for the direct bury		
Production length on spool (700x370mm)	1250m		
Weight	approx. 0.030 kg/m		
Total weight	approx. 50 kg (including spool)		
Min. bending radius	guided bending: R = 65mm		
(according to DIN EN 61386-24)	free bending: R = 10 x speedpipe-outer diameter		
Transport and storage temperatures	-40 to +70	°C	
Laying or assembly temperature	-10 to +50	°C	
Operating temperature	-40 to +70	°C	
	Temperature at which the full functionality of the installed or laid components is given		
UV resistance (DIN EN ISO 4892-1)	3 years (south-european climate)		

For installation follow the installation instruction and the laying instruction!

Technical data			
Quality	Value	Unit	
Material Material			
Material	PolyEthylen PE-HD, regenerate- and recyclate-free		
MFI (according to DIN 8075)	max. 30	%	
Homogeneity	free from inclusions < 0.02	mm ²	
Internal pressure creep rupture test (DIN 16874)	Sigma 4.0 for 170h at 80°C	N/mm ²	
Fire behavior (DIN EN 13501-1)	E		
speedpipe-ground 7x1.5			
Dimension	$D = 7.0^{+0.1}$; $s = 1.5^{+0.1}$	mm	
Colour of stripes	orange opposite transparent windows		
Pressure nominal	PN 16		
Inner surface	32 optimized sliding ribs		
Burst pressure	min. 60	bar at 20°C	
Max. recommended tensile strength	250	N at 20°C	
Tensile strength at break	450	N at 20°C	
Apex pressure (according to DIN EN 61386-24)	2500	N at 20°C	

gabocom is certified by the quality system following DIN EN ISO 9001, the environmental management system DIN EN ISO 14001 and the energy management system DIN EN 50001.

The used materials meet the Reach default (EU regulation 1907/2006) and the RoHS default (EU guidelines 2011/65).

gabo Systemtechnik GmbH Tel. +49 9962 950-200 Editor: AF
Am Schaidweg 7 Fax +49 9962 950-202 Release: MK
94559 Niederwinkling info@gabocom.com Date: 10.02.2021
GERMANY www.gabocom.com Edition: 4

No responsibility is taken for the currency and completeness of details and information. This document can be revised and supplemented without prior notice. Liability for damages is excluded.